

# The Cold Spray Coating Process: A Future Technique in Material Deposition

Ripandeep Singh<sup>1</sup>, Gurpreet Singh<sup>2</sup> and Hazoor Singh Sidhu<sup>3</sup>

<sup>1</sup>Research Scholar, Punjabi University Patiala, Punjab, India

<sup>2</sup>Assistant Professor, Dept. Mechanical Engineering, Punjabi University Patial, India

<sup>3</sup>Professor, Dept. Mechanical Engineering, YCoE Talwandi Saboo, Punjabi University Patial, India

Email: er.ripandeepsidhu@gmail.com

(Received 10 November 2015; Accepted 23 December 2015; Available online 2 January 2016)

**Abstract** - Cold Spray coatings is a material deposition technique from the broad family of thermal spray coatings with the difference of depositing spray particles at the temperature below melting point as it is a solid state process. The spray particles are impinged on the substrate with supersonic velocities. This paper imparts some light on application of this emerging technique with pros and cons. As this technique come up from last 20 years yet practical area is limited and confined to some research only. As this is a quite beneficial technique and help require from public/private sector to commercialize this technique and hope in coming years it comes up with a good growth in this area.

**Keywords:** Cold spray, coatings

## I. INTRODUCTION

An emerging solid state process quickly being adopted by many researchers and industries. It is capable of enhancing the various properties of substrate without effecting the original properties and there are no undesirable effects of process temperatures [1]. Cold spray is very much capable for coatings on various surfaces of different materials e: g Metals, Polymers and Composites etc. It also have the ability to prevent oxidation, residual thermal stresses, vaporization, etc. [3] Cold Spray finds attractive in industries working on advanced materials, such as nanotechnology.

It is a new tool introduced in the field of thermal spray coatings. Cold spray is also known by various names as Cold Gas Dynamic Spray, Gas Dynamic Spray, Kinetic Energy Metallization, and Kinetic Spraying. As a part of thermal spray coatings, Cold Spray produces coatings for large number of applications [1-4]. However cold spray produces coatings on wide range of materials at much lower temperatures and without any thermal effects [6]. This article reviews evolution, technology, applications and benefits of the most advanced / latest technique Cold Spray.

## II. HISTORY

Thermal spray consists of a family of coating processes which are used for coating of metallic and non-metallic materials to different metal substrates [8]. In traditional processes, molten particulates formed from feedstock

material (typically in powder, wire, or rod form) by combustion or electric arcing, which are then gathered and accelerated toward the substrate by a jet of hot gas [7]. The particles become splat when they strike on the substrate material and adhere to the substrate and upon solidification making a solid joint [9]. Thermal spray invented in late 1800s and was commonly known as flame spraying and was primarily used for applying protective coatings and to restore worn metal parts. It gain importance during and after World War II when thermal spray is widely used to repair tank and aircraft components [13-16]. Today, the number of applications for thermal spray is countless as they are widely used to improve nearly all properties of materials e: g resistance to corrosion, elevated temperatures, oxidation, and wear, etc. [18-19] Thermal spray found applications in power generation, aerospace, automotive, medical, heavy equipment, nuclear.

## III. HOW DIFFERENT IS THE COLD SPRAY

Traditional thermal spray technology can produce coatings of high-quality on variety of materials, but due to their high process temperatures the deposits and substrates are exposed to oxidation, metallurgical transformations, and residual thermal stresses caused by the uncontrolled solidification rates of individual particles as they hit the substrate. It was the group of Russian researchers in 1980s at the invention of cold spray is credited to a group of Russian researchers working in the Institute of Theoretical and Applied Mechanics at the Russian Academy of Sciences in Novosibirsk. [20]. they demonstrated that the bonding of small particles (1-50 microns) on substrate could occur when they are imparted at supersonic velocities and forms a bond. This is how the cold spray differs from traditional thermal spray processes where particle velocities are generally lower, but particle temperatures can be quite high, as illustrated in Fig. 1




Fig. 1 Process temperatures and particle velocities of various coating processes [6]

#### IV. HOW DOES COLD SPRAY WORK




Fig.2 Setup of cold spray coating

In one setup (Fig. 2), the gases (helium or nitrogen) at high pressure is injected into a chamber under pressure and heated to 300°-700°C – which doesn't heat the particles, but used to increase the velocity of gas jet. Particles are feed through Powder feedstock into the gas stream, which is not hot enough to melt the particles. The powder/gas mixture is then passed through nozzle where the particles are accelerated to supersonic velocities [21]. The particles at supersonic speeds impact the substrate with enough kinetic energy to produce mechanical/metallurgical bonding without melting and/or solidification. Upon deposition, there are very small microstructural changes, in Fig. 3.




Fig. 3 Left: Particles of AA2618 aluminium alloy with equiaxed (top left) and columnar (bottom left) grain structures. Right: Cold spray deposit produced with a blend of these two powders showing the preservation of the original grain structure for each of the powder constituents (Ref. 5) (Photo courtesy of the University of Ottawa, Canada.)

For different material, there are different range of supersonic velocities for the bonding, if the velocities are above the range, the deposition efficiency is considerably high and if it is below this critical velocity range, then the particles are likely to cause some irregularities i.e surface erosion due deflection of particles.

The critical velocity ranges for pure metals such as Cu, Fe, Ni, and Al have been estimated at greater than 550 m/s [21]. In an advancement of this technology [22], the position of the powder feedstock is made downstream into the nozzle (Fig. 4).

This eliminates the requirement for injecting powder into a pressurized compartment and avoids potential nozzle erosion and clogging. Only clean dry air at 80-90 lb/in is required for its operation. The air is preheated to 200°-400°C inside DYMETTM gun [22] to increase the velocity to supersonic velocities at the diverging section of the nozzle.




Fig.4 Schematic diagram of a variant of the cold spray process, where the powder is injected downstream in the DeLaval nozzle [22].

By using this method, a wide selection of materials can be deposited, including metal mixtures, metal alloys, cermets, epoxy resins, polyurethane, and thermoplastic polymers, over wide range of substrates [29-30].

#### V. APPLICATIONS

Cold spray technology is an advancement of well-established thermal spray coatings enhancing the scope and methods of coatings. The various applications of cold spray technology are in Table 1[15-25].

TABLE I THE VARIOUS APPLICATIONS OF COLD SPRAY TECHNOLOGY

| Applications                                 | Examples  |
|--|---|
| Metal restoration and sealing                | Engine blocks, castings, molds, dies, weld joints, auto body, HV AC, refrigeration, cryogenic equipment, heat exchangers [22]   |
| Thermal barriers                             | Aluminium piston heads, manifolds, disc brakes, aircraft engine components  |
| Heat dissipation                             | Cu or Al coatings on heat sinks for microelectronics  |
| Soldering priming                            | Microelectronics components and printed circuit boards  |
| Electrically conductive coatings             | Cu or Al patches on metal, ceramic, or polymeric components [12]  |
| Dielectric coatings                          | Ceramic coatings for aerospace, automotive, and electronic packaging  |
| Antistick properties                         | Deposits Impregnated with release agents such as PTFE or silicone   |
| Friction coatings                            | Rolls for papermaking   |
| Localized corrosion protection               | Zn or Al deposits on affected helms, weldments, or other joints in which the original protective layer has been affected by the manufacturing process   |
| Rapid prototyping and near-net manufacturing | Well-defined footprints. Fabrication of parts with custom composite or gradient structures  |
| Biomedical                                   | Biocompatible/bioactive materials on orthopedic implants, prostheses, dental implants. Porous coatings of these materials on load-bearing implant devices facilitate implant fixation and bone in. growth, replacing cements and screws |
| Wear-resistant and decorative coatings       | Numerous applications   |

**VI. SUMMARY**

Cold spray coating is future and an advancement of coating processes. This is not the replacement of the existing processes but an additional process to enhance the processes. Cold spray coatings has a huge benefits in coating of boilers and incinerators to increase there life by preventing them from various defects . It is expected that the coming years see the progressive growth of this process.

**VII. ACKNOWLEDGMENT**

The author ‘Ripandeep Singh’ thankfully acknowledges the supervisors ( Dr.Gurpreet Singh and Prof. Dr. Hazoor Singh Sidhu) to motivate to do work in the area of thermal spray coatings.

**REFERENCES**

[1] Lupoi R, O'Neill W (2011) Powder stream characteristics in cold spray nozzles. *Surf Coat Technol* 206:1069–1076

[2] Lupoi R, O'Neill W (2010) Deposition of metallic coatings on polymer surfaces using cold spray. *Surf Coat Technol* 205: 2167–2173

[3] Irissou E, Legoux J-G, Ryabinin AN, Jodoin B, Moreau C (2008) Review on cold spray process and technology: part I—intellectual property. *J Therm Spray Technol* 17(4):495–516

[4] Villafurte J (2010) Current and future applications of cold spray technology. *Metalfinishing* 108(1):37–39

[5] Choudhuri A, Mohanty PS, Karthikeyan J (2009) Bio-ceramic composite coatings by cold spray technology. In: *Thermal Spray:*

Expanding thermal spray performance to new markets and applications (ASM International), pp 391–396

[6] Papyrin AN (2006) Cold spray: state of the art and applications. *Cold spray technology*, Albuquerque, pp 1–21

[7] Tinashe SE (2010) Conceptual design of a low pressure cold gas dynamic spray (LPCGDS) system. M.S. Thesis

[8] Karthikeyan J (2004) Cold spray technology: International status and USA efforts. Report by ASB Industries Inc.

[9] Shkodkin A (2010) Peculiarities of the gas dynamic spray applications in Russia. OPCS, Russia

[10] Karthikeyan J (2006) Evolution of cold spray technology. *Adv Mater Process* 164(5):66–67

[11] Thurston SH (1902) Method of impacting one metal upon another. US706701, (year of priority 1900)

[12] Thurston SH (1902) Process of coating one metal with another metal. US706702 (year of priority 1901)

[13] Rocheville CF (1963) Device for treating the surface of a workpiece. US3100724 (year of priority 1958)

[14] Papyrin A, Kosarev V, Klinkov KV, Alkhimov A, Fomin VM (2006) Cold spray technology. Elsevier, Oxford

[15] Alkhimov AP, Kosarev VF, Nesterovich NI, Papyrin AN (1991) Method for deposition of coatings. SU1618778 (year of priority 1986)

[16] Alkhimov AP, Nesterovich NI, Papyrin AN, Kosarev VF, ShushpanovMM(1991) Device for applying coatings. SU1618777 (year of priority 1986)

[17] Kosarev VF, Klinkov SV, Sova AA (2007) Recently patented facilities and applications in cold spray engineering. *Recent Patents Eng* 1:35–42

[18] Maev RGr, Leshchynsky V, (2008) Introduction to low pressure gas dynamic spray. In: *Physics and technology*. Wiley-VCH, Weinheim doi:10.1002/9783527621903

[19] Heinrich P, Kreye H, Richter P, Stoltenhoff T, Richter H (2006) Method and system for cold gas spraying. US7143967

[20] Alkhimov, A. P., Kosarev, B. F., and Papyrin, A. N. 1990. A method of cold gas dynamic deposition. *Dokl. Akad. Nauk SSR* 315, pp. 1062-1065

[21] Alkhimov, A. P., Papyrin, A. N., Kosarev, V. F., Nesterovich, N. I., and Shushpanov, M. M. 1994. Gas-dynamic spraying method for applying a coating. U.S.Patent 5,302,414.

[22] Kashirin, A. I., Klyuev, O. F., and Buzdygar, T. V. 2002. Apparatus for gasdynamic coating. U.S. Patent 6,402,050

[23] Kumar S, Gyuyeol B, Changhee L (2009) Deposition characteristics of copper particles on roughened substrates through kinetic spraying. *Appl Surf Sci* 255:3472–3479

[24] Sidhu TS (2006) Ph.D. Thesis

[25] Li C-J, Wang H-T, Zhang Q, Yang G-J, Li W-Y, Lio HL (2010) Influence of spray materials and their surface oxidation on the critical velocity in cold spraying. *J Therm Spray Technol* 19(1–2):95–101

[26] Li C-J, Li W-Y (2003) Deposition characteristics of titanium coating in cold spraying. *Surf Coat Technol* 167:278–283

Li C-J, Li W-Y, Wang Y-Y, Yang G-J, Fukunuma H (2005) A theoretical model for prediction of deposition efficiency in cold spraying. *Thin Solid Films* 489:79–85

[27] Li C-J, Li W-Y, Lio H (2006) Examination of the critical velocity for deposition of particles in cold spraying. *J Therm Spray Technol* 15(2):212–222

[28] Yoon S, Lee C, Choi H, Jo H (2006) Kinetic spraying deposition behavior of bulk amorphous NiTiZrSiSn feedstock. *Mater Sci Eng* 415:45–52

[29] Legoux J-G, Irissou E, Desaulniers S, Boby J, Harvey B, Wong W, Gagnon E, Yue S (2010) Characterization and performance evaluation of a helium recovery system designed for cold spraying. In: *International thermal spray conference and exposition, Thermal Spray: Global Solutions for Future Application (DVS-ASM)*, pp 560-565

[30] Maev, R. G., Strumban, E., Leshchynsky, V., and Beneteau, M. 2004. Supersonic induced mechanical alloy technology and coatings for automotive and aerospace applications. Presentation at TSS Cold Spray 2004, Akron, Ohio

[31] Balani K, Agarwal A, Seal S, Karthikeyan J (2005) Transmission electron microscopy of cold sprayed 1100 aluminum coating. *Scripta Mater* 53:845–850